Loss Prevention Standards – Asset Classes

Security of Glazing

Version: 1.1 Date: 29th October 2024

This document provides guidance on the types of glazing materials available, as poorly secured and maintained windows can be vulnerable to forced entry and may increase the risk of theft or vandalism.



Security of Glazing



Introduction

One of the most common means of gaining unauthorised entry into otherwise secure premises is the breakage of glazing, followed by the opening or forcing of any securing locks or catches.

This is often made easier by the fact that most glass used to glaze windows and doors is quickly and easily broken, but this does not have to be so. This document outlines various types of glazing material available and comments on their respective strengths or weaknesses.



General Considerations

Various types of glazing material are available, e.g. glass or plastics. Types of glass are generally categorised by the method of manufacture, i.e. float glass, toughened glass or laminated glass; but for each type of glass different constituent materials may be used. As an example, soda lime is the most common type of glass, but for specialist applications borosilicate or alkaline earth silicate may be used.

Whatever its type, for effective security all glazing needs to have appropriately designed and built frames/surrounds which are then maintained in good condition. To help achieve this, the services of a competent glazier should always be sought when installing new or upgraded glazing, e.g. by using a member of the Glass and Glazing Federation (GGF).

As a guide, when choosing glazing, the following aspects also need consideration:

Do not consider security of glazing in isolation. Look at your security in a joined-up way and consider other potential weak points in the building perimeter

- When choosing a type of glass best suited to your security requirements, do not overlook the need to comply with any requirements that may relate to fire precautions or life safety
- Do not place undue 'blind' faith in double glazing as a security measure, as this uses normal float glass and does not significantly improve the security
- Glazing rebates should be considered and need to be deep enough to adequately hold any 'improved' glazing material in place, e.g. laminated glass usually requires a minimum rebate of 15mm to ensure it remains in place when under attack
- Glazing should ideally be internally fixed into its frame. Externally fixed glazing is inevitably more vulnerable to removal, and if glazing is externally fixed, you should be aware that:

 Putty or glazing compound is soft when new and requires considerable time to harden
 Note: Once the glazing compound is hardened and provided it and the frame remain in good condition, puttied glazing is usually difficult to remove
 - Beading strips may be inherently weak. In any event they derive their strength from the means and number of fixings
 - The use of glass sealant or security glazing tape can improve the security of external beading
- Glazed openings should have locks and catches fitted, which should be strong enough and arranged to withstand being prized open from the outside or should the glazing be broken being opened from the inside

Refer to the two *Aviva Loss Prevention Standards on Security Doors and Windows* and *Locks* which provide further quidance in this area.

LOSS PREVENTION STANDARDS



Security Qualities of Various Types of Glazing

Various types of glass may be used to glaze windows and doors, such as:

Float or Annealed Glass

This is the most frequently used glass and it is supplied in a range of thickness from 2 to 15mm, with 4mm being the most common. Float glass above 8mm thick is often referred to as plate glass and is usually used for fixed

shop-front windows. Thicker sizes can provide some increase in resistance to breakage, but that depends on the size of the glazed pane and its arrangement.

One good feature of float glass is that if it is broken, any window locks cannot be easily overcome. Intruders require time to break-out most of the remaining pieces of glass to allow safe entry.

For safety reasons (not security), float glass is sometimes retro fitted with plastic 'Applied Safety Film'. Ideally this film is a type designed to meet the requirements of BS 6206 or BS EN 12600.

- BS 6206:1981 Specification for impact performance requirements for flat safety glass and safety plastics for use in buildings
- BS EN 12600:2002 Glass in building. Pendulum test. Impact test method and classification for flat glass

Safety film is designed to hold the glass pieces together in the event of breakage, thus reducing the risk of personal injury. A benefit is that it can also enhance security to a limited degree as it hinders breakage, helps retain broken panes within a frame and can slow down removal of the glass fragments and therefore access via the glazed area.

Glass Bricks

These are made of float glass and cast into blocks resembling hollow bricks. These are generally constructed like a wall and cemented or grouted in place. Properly installed they can create a very strong glazed area.

Wired (Georgian Wired) Glass

This glass has a fine steel mesh sandwiched between two molten layers of glass during its manufacture. It is intended as a fire-resistant material, the mesh holding the glass together in the event of a fire.

Although often fitted as secure glazing, such glass is only marginally more resistant to breakage than float glass. It is however harder to break a wired glass pane completely out of its frame, e.g. to gain full entry, and the mesh may act as a visual deterrent to breakage.

Toughened/Tempered (Safety) Glass

This glass has been subjected to a special heat treatment after being cut to size, and the process is designed to improve the safety of the glass when it breaks.

Whilst more resistant to breakage than float glass when hit by a large soft object, e.g. accidental impact by a person, when hit by a small sharp object it is very easily broken, which is why small pointed hammers are provided adjacent to toughened glass windows in areas on trains and coaches to facilitate emergency exit.

Once a pane of toughened glass is broken it shatters into hundreds of tiny cubes, which then can be easily and quickly knocked out of the frame to create a smooth opening.

LOSS PREVENTION STANDARDS



Laminated Glass

This is the only glass generally recognised as providing security glazing. It can be made by assembling two or more pieces of float glass, one each side of an interlayer of thin Polyvinyl butyral (PVB) resin. It comes in various thicknesses (grades), with the thicker grades containing more layers of glass and interstitial layers of PVB. The current manufacturing standard for laminated glass is <u>BS EN 14449:2005 - Glass in building. Laminated glass and laminated safety glass. Evaluation of conformity/product standard.</u>

When attacked, laminated glass resists being broken, but more significantly, the PVB interlayer helps prevent an opening being made.

The more common grades are as follows:

- Safety Glass: 6.4 6.8mm. Intended mainly as basic safety glass. It can nonetheless provide reasonable resistance to forced entry, being stronger than float or toughened glass
- Burglary Resistant Glass: 7.5 13.5mm. Intended as burglary resistant glass. This can provide considerable
 resistance to forced entry, according to the risk level of BS EN 356 used, e.g. P1A P5A (impact) and/or P6B P8B (hammer and axe attack). Note: Such glass needs to be installed within an appropriate security glazing
 frame
 - o <u>BS EN 356:2000 Glass in building. Security glazing. Testing and classification of resistance against manual</u> attack
- Bullet Resistant Glass: 30mm upwards. Intended as bullet resistant glass. This is a specialist area for which suitable professional advice should be sought. A risk level should be selected according to those described in BS EN 1063 which specifies the test requirements for bullet resistant glass
 - o BS EN 1063:2000 Glass in building. Security glazing. Testing and classification of resistance against bullet attack

Other benefits of laminated glass are:

- Aesthetics and Design It can be coloured or patterned
- Ease of Use It can be cut to size
- Ultraviolet Radiation Protection The PVB interlayer filters out ultraviolet radiation from sunshine, which helps reduce colour fading/bleaching of any items in line of sight of the sunlight and other related ultraviolet issues
- Contamination Protection When broken the glass is held in place, and glass fragments may not fall onto and damage or contaminate any items in close proximity to the glass

For safety critical applications, laminated glass can be made from toughened glass. When this form is required, a poured resin material is used as the interlayer instead of PVB. The glass is sometimes referred to as Resin Compound Glass.

LOSS PREVENTION STANDARDS



Plastic Glazing

Various types of plastic sheet are potentially suitable for glazing, e.g. cast or extruded acrylic, polystyrene or polycarbonate sheet. Some of these can be supplied with Glass Reinforced Plastic (GRP)/fibreglass or metal mesh reinforcement to help prevent breakage.

Whilst some plastics have better resistance to breakage than float glass, there are some disadvantages to using plastic materials for glazing, such as:

- Combustibility they are combustible
- Poor optical clarity (polycarbonate)
- Poor light transmission (GRP or metal mesh reinforced plastic)
- Vulnerability to scratching
- Can be easily compromised by a saw or a flame
- Potential loss of strength and/or cloudiness caused due to the effects of ultraviolet radiation from exposure to sunshine

Polycarbonate is probably the most useful of these plastics, as it has good impact resistance, e.g. it is used in police riot shields, it has reasonable optical clarity and is available in sheets of varying thicknesses. However, it flexes under sustained impact or attack and, if it is to remain securely in place, careful fixing is required.

For reasons of appearance, plastic glazing is usually only used at industrial premises. Its use should be carefully considered and any proposals should be discussed with your Insurer or Broker.

Identifying Installed Glass

Over the years different standards have been in force and applied to glass, some of which have been mentioned above. In some cases, the manufacturer or the installer will have voluntarily applied an indelible mark or label to their glass, but legal requirements to mark glass only exist when the glass is installed in particular 'safety critical locations'. This is as defined by the relevant Health and Safety Regulations and/or Building Regulations.

Identifying installed glass and any related legal safety requirements is not straightforward, so to reiterate previous advice, reference should always be made to a competent glazier when reviewing glazing matters.

It is always recommended to have up to date drawings and specifications of a building, therefore, if an investment has been made in special glazing or enhanced security features, then these should be clearly documented in site drawings and associated documentation.

Some general information on identifying glazing can be found in the RISCAuthority (the UK Insurer's technical advice body) publication: S24 – Physical Security for Homes: Guidance for Occupiers.

LOSS PREVENTION STANDARDS



Checklist

A generic Security of Glazing Checklist is presented in Appendix 1 which can be tailored to your own organisation.

Specialist Partner Solutions

Aviva Risk Management Solutions can offer access to a wide range of risk management products and services at preferential rates via our network of Specialist Partners.

For more information please visit:

Aviva Risk Management Solutions - Specialist Partners

Sources and Useful Links

- The British Standards Institution
- RISCAuthority
- British Security Industry Association (BSIA)
- BS 5375:2007 Code of practice for installation and application of security glazing
- PAS 24:2016 Enhanced security performance requirements for doorsets and windows in the UK

Additional Information

Relevant Loss Prevention Standards include:

- Intruder Alarms European Standards
- Intruder and Hold Up Alarms
- Property Video Surveillance Systems
- Locks Security
- Security: Doors and Windows

To find out more, please visit Aviva Risk Management Solutions or speak to one of our advisors.

Email us at riskadvice@aviva.com or call 0345 366 6666.*

*The cost of calls to 03 prefixed numbers are charged at national call rates (charges may vary dependent on your network provider) and are usually included in inclusive minute plans from landlines and mobiles. For our joint protection telephone calls may be recorded and/or monitored.

LOSS PREVENTION STANDARDS

Appendix 1 – Glazing Checklist



Location	
Date	
Completed by (name and signature)	

	Title	Y/N	Comments
1.	Has a risk assessment been undertaken of the current physical security at your premises, including the following?		
	 Local history of security related events? Nature of contents/occupancy, especially close to each opening and its attractiveness to theft? Accessibility of the area for criminals? Provision of anything that could improve access to upper levels of the building/roof? Strength and nature of the building construction in comparison to any doors/windows and securing mechanisms? The nature of any other electronic security measures or human presence on site? 		
2.	Has independent crime prevention advice been sort from:		
	The Police?A security consultant?Your insurer?		
3.	 Have you checked whether your Insurer has applied a Minimum Security Standard/Condition? If one does do your existing locks and wider security arrangements comply with the Minimum Security Standard? If not do you have formal insurer agreement for any alternative arrangements? Are these clearly described? Are these audited against? 		

		Title	Y/N	Comments	
LOSS PREVENTION STANDARDS					



4.	 Have you checked the nature and type of your glazing? Is this formally recorded with up to date drawings and specifications maintained on site? Does your glazing provide the appropriate level of security based on the security risk? o Does it also meet any fire or life safety criteria? 	
5.	Do you audit the glazing, frames/surrounds and fixings to ensure they are appropriately: Designed? Installed? Inspected and maintained in good condition?	
6.	Are glazed openings fitted with any additional physical security devices?	
7.	Have you considered improving the glazing as part of a set of joined-up and robust security measures?	
8.	Do you seek professional advice and use competent installers, e.g. a member of the GGF, when reviewing or installing new or upgrading any glazing? Is this part of your Management of Change procedure?	
9.	Are security arrangements and the basis for the risk assessment reviewed following any security issues; local incidents; intrusions or losses? Note: If not, you may be at more risk of a repeat incident.	
10.	Additional comments:	

LOSS PREVENTION STANDARDS



Please Note

This document contains general information and guidance only and may be superseded and/or subject to amendment without further notice. Aviva has no liability to any third parties arising out of ARMS' communications whatsoever (including Loss Prevention Standards), and nor shall any third party rely on them. Other than liability which cannot be excluded by law, Aviva shall not be liable to any person for any indirect, special, consequential or other losses or damages of whatsoever kind arising out of access to, or use of, or reliance on anything contained in ARMS' communications. The document may not cover every risk, exposure or hazard that may arise and Aviva recommend that you obtain specific advice relevant to the circumstances.

29th October 2024

Version 1.1

ARMSGI1432020

Aviva Insurance Limited, Registered in Scotland Number SC002116. Registered Office: Pitheavlis, Perth PH2 0NH.

Authorised by the Prudential Regulation Authority and regulated by the Financial Conduct Authority and the Prudential Regulation Authority.

LOSS PREVENTION STANDARDS